

Truguard Microporous Basecoat

DESCRIPTION

Truguard Microporous Basecoat provides the foundation for Leyland's high performance, flexible Truguard Microporous Gloss system.

USES

Particularly suitable for the long-term protection and decoration of exterior timber surfaces, when used in conjunction with Leyland Truguard Microporous Gloss. Suitable for application to bare timber both softwood and hardwood and to surfaces which have been previously decorated with preservative woodstains.

RECOMMENDED USES

Exterior.

TYPE OF SUBSTRATE

Wood and masonry surfaces.

COLOUR RANGE

For colour availability, please refer to Leyland Trade Colour Range.

FINISH

Eggshell.

COVERAGE

Approximately 12 square metres per litre depending on the nature and porosity of the surface being painted.

DRYING TIME

Touch dry in 4-6 hours. Recoatable after 16-24 hours.

TRANSPORTATION & STORAGE

To avoid the risk of spillage, always store and transport in a secure upright position.

STORE AWAY FROM HEAT AND FLAME.

THINNER

White Spirit.

PREPARATION

All surfaces to be painted should be sound, dry, clean and free from dust and grease.

BAREWOOD: Ensure the wood has a moisture content of less than 20%. Treat knots and resinous areas with Knotting Solution. Apply one coat of a clear preservative to all bare timber paying particular attention to end grain and joints. Apply one coat of Microporous Basecoat followed by two coats of Microporous Gloss.

BARE METAL: Remove any rust and corrosion and apply a suitable metal primer. Apply one coat of Microporous Basecoat followed by two coats of Microporous Gloss allowing 16-24 hours between coats.

PREVIOUSLY PAINTED SURFACES UNSOUND

CONDITION: Remove all existing coatings using a hot air stripper or a Paint & Varnish Remover. Rub down the

bare timber using abrasive paper - leaving it in a clean and smooth condition. Then treat timber as per **BAREWOOD**. Special precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead. For further advice contact Technical Advisory.

SOUND CONDITION: Lightly abrade with fine waterproof abrasive paper and rinse thoroughly. Avoid the inhalation of dust. Wear a suitable face mask if dry sanding. Apply one coat of Microporous Basecoat followed by two coats of Microporous Gloss, allowing 16-24 hours between coats. For maximum protection apply to bare timber.

APPLICATION

Stir well before use. Apply two full coats, allowing 16 - 24 hours between coats under normal drying conditions.

CLEANING

Remove as much product as possible from application equipment before washing. Replace lid firmly. Wash equipment immediately after use with White Spirit or Turpentine Substitute. Some local authorities have special facilities for the disposal of waste coatings. Do not empty product into drains or watercourses.

PRECAUTIONS

PAINT PRODUCT

FLAMMABLE

Contains Ethyl Methyl Ketoxime.

May produce an allergic reaction.

Repeated exposure may cause skin dryness or cracking.

Keep away from sources of ignition - No Smoking.

Ensure maximum ventilation during application and drying.

Avoid contact with skin and eyes.

In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.

After contact with skin, wash immediately with plenty of soap and water or a recognised skin cleaner - **DO NOT USE SOLVENT OR THINNERS.**

When spraying, do not breathe spray, wear suitable respiratory protective equipment.

If swallowed seek medical advice immediately and show the container or label.

Keep out of reach of children.

PROFESSIONAL DECORATORS

Safety data sheet available for professional user on request.

VOC CONTENT

HIGH VOC CONTENT 25-50%

VOC's (Volatile Organic Compounds) contribute to atmospheric pollution.

Manufactured under a quality system approved by the BSI.

Issue Date: 03/02

Kalon Decorative Products, Huddersfield Road, Birstall, Batley, West Yorkshire. WF17 9XA.

Telephone: 01924 354000 Facsimile: 01924 354001